



King & King Enterprises  
P.O. Box 1275  
Minneola, Florida 34755

## TEAK MINUS - TEAK PLUS

**TEAK MINUS** is the first product of a two part teak cleaning system.

**TEAK PLUS** is the second product of a two part teak cleaning system.

Do not try and reverse this way of using these products.

It is always best to find the specific dilution for using these products on your job. Test them on the yacht you desire to clean. In this way, you save money, time, energy, and will not damage any of the surfaces you are working on.

**Caution:** Both of these products contain hazardous materials that can by themselves, do damage to the eyes and skin, metals, and uncured varnishes. (In the case of less than 30 day cured varnishes and paints, dilutions vary considerably -- 5-10 parts water to 1 part MINUS and PLUS), especially do not get these products on anodized aluminium. If you do, call us at 352 394 0664, we manufacture a product to reclaim the high shine on the anodize as well as it can be accomplished by not re-anodizing it. There is a system to treating this and other metals that come in contact with teak decks in order to avoid this type of problem.

When using **TEAK MINUS**, **always keep vinegar, orange or apple juice** around (in an emergency) to neutralize the product when it gets on the skin. Then rinse until the skin is no longer slippery.

When using **TEAK PLUS**, **simply rinse the skin with plenty of water only.**

If either of these products get in the eyes, rinse with water for 15 minutes, and call a physician.

Just remember, follow the directions and you will have no danger or damage using these products. Always be a responsible person and take care of yourself. If you do not understand how to use or be safe with these products, call your sales person and he will explain what you need to know.

### **BASIC APPLICATION:**

Dilute TEAK MINUS 1 part MINUS to 3 parts water for heavy cleaning of teak decks. Apply product to teak and use a ¾ inch 3M **green scrub** pad, or a medium bristle brush. Spread the product over 3 to 4 square feet at a time (no more please). Allow to **soak from 3-5 minutes**. Scrub area thoroughly. The wood will turn dark, after scrubbing, **Do Not, Do Not! rinse at this time. Apply TEAK PLUS** as it comes from the container – **full strength**. When the teak looks natural in colour, rinse completely with water. At this point, survey your work and determine whether or not there is a complete bleaching and there are not dark or shaded spots. If the deck is slightly spotted, dilute the TEAK PLUS 3 parts water to 1 part TEAK PLUS, apply this solution to the deck and allow it to set for 3 to 5 minutes, then rinse for best results.

Always keep water running on the painted surfaces and metal, and water line. Do not get either of these products on the lettering on the aft end of the yacht when you are cleaning the teak around that area of the boat. Keep water running on the lettering. Enamel paints are generally used to paint on these letters, or gold leaf. They will not hold up under any teak cleaners.

King & King Enterprises take no responsibility for use, storage, or liability in use of these products. Never mix chemicals... keep all chemicals out of reach of children and animals.

Do not store these materials in areas that reach over 70 degrees F. Store them in plastic containers if possible.

Please be safe – alert – cautious.